

# CHEVRON HYDRAULIC OIL AW 32, 46, 68

# **PRODUCT DESCRIPTION**

Chevron Hydraulic Oils AW are designed to give excellent hydraulic pump protection.

# **CUSTOMER BENEFITS**

Chevron Hydraulic Oils AW deliver value through:

- **Good oxidation stability** Provide good service life in high pressure service.
- Rust and corrosion protection Give excellent protection against corrosion of both copper and steel, and passes the ASTM D665A distilled water rust test and ASTM D665B synthetic sea water rust test.
- Minimum viscosity change over a wide temperature range.
- Good foam inhibition Contain special foam suppressant, minimizing both foaming and aeration problems.
- · Excellent antiwear properties
- Meets major pump manufacturer's requirements ISO 32, 46, and 68 meet the requirements of leading hydraulic pump manufacturers for antiwear-type hydraulic fluids in both vane- and piston-type pumps.
- Good stability in the presence of water by ASTM D2619 Hydrolytic Stability test and the Denison hybrid T6H2OC Wet Pump test.
- Good thermal stability in the presence of copper and steel by the MAG Cincinnati Machine Thermal Stability, Procedure A, test.
- **Fast water separation** Minimize rust problems by fast release of water.

### **FEATURES**

Chevron Hydraulic Oils AW are formulated with refined paraffinic base oils. They provide excellent antiwear protection, oxidation and corrosion inhibition, as well as foam and aeration suppression. All grades have excellent demulsibility characteristics.

Hydraulic systems, due to the nature of their operation, experience accelerated wear unless they are protected by clean, high quality antiwear hydraulic oils. Surging pressures in pumps and valves can increase metal-to-metal contact unless antiwear protection is present. The antiwear additives in Chevron Hydraulic Oils AW create a protective film on the metal surfaces. This protective film minimizes metal-to-metal contact, which is most severe in vane- and gear-type pumps. As hydraulic pressures increase over 1000 psi, the need for antiwear protection increases proportionally.

# **APPLICATIONS**

Chevron Hydraulic Oils AW are versatile lubricants available in ISO viscosity grades 32, 46 and 68.

**ISO 32**, **46**, and **68** grades are most commonly used for hydraulics with vane-, piston-, or gear-type pumps, especially where pressures exceed 1000 psi. They can also be used to lubricate lightly loaded reciprocating compressors.

Product(s) manufactured in the USA.

Always confirm that the product selected is consistent with the original equipment manufacturer's recommendation for the equipment operating conditions and customer's maintenance practices.

A **Chevron** company product

27 October 2014

IO-110

Chevron Hydraulic Oils AW 32, 46, and 68:

- meet major pump manufacturer requirements including Eaton-Vickers 35VO25A for M-2950-S (Mobile) and I-286-S (Stationary), Parker Hannifin (Denison) HF0/HF2/T6H20C, and **Bosch Rexroth Racine Model S**
- meet ASTM D6158 HM
- meet **DIN** 51524-2
- meet ISO 11158 L-HM
- meet MAG Cincinnati, Cincinnati Machine specifications P-68 (ISO 32), P-70 (ISO 46), and P-69 (ISO 68)

• are registered by **NSF** and are acceptable as lubricants where there is no possibility of food contact (H2) in and around food processing areas. The NSF Nonfood Compounds Registration Program is a continuation of the USDA product approval and listing program, which is based on meeting regulatory requirements of appropriate use, ingredient review and labeling verification.

Please consult with your equipment manufacturer if equipment is operating outside normal operating conditions. Do not use in high pressure systems in the vicinity of flames, sparks and hot surfaces. Use only in well ventilated areas. Keep container closed.

# TYPICAL TEST DATA

ISO Grade	32	46	68
Product Number	255675	255674	255673
SDS Number	7457	7457	7457
API Gravity	32.6	31.8	31.6
Viscosity, Kinematic cSt at 40°C cSt at 100°C	30.4 5.2	43.7 6.5	64.6 8.4
Viscosity, Saybolt SUS at 100°F SUS at 210°F	157 44	225 48	334 55
Viscosity Index	98	98	99
Flash Point, °C(°F)	220(428)	226(439)	235(455)
Pour Point, °C(°F)	-25(-13)	-23(-9)	-22(-8)
Oxidation Stability Hours to 2.0 mg KOH/g acid number, ASTM D943	>2000	>2000	>2000

Minor variations in product typical test data are to be expected in normal manufacturing.